

Serial No. 10/827,174

Art Unit: 1762

Amendments to the Claims

1. (Currently Amended) A method of manufacturing metal wire rod for use in plastic working comprising:
 - a. cleaning metal wire rod by at least one cleaning process of anodic pickling and/or cathodic pickling for 20 seconds or less;
 - b. contacting the metal wire rod for 5 seconds or less with an aqueous, lubricating-coating formation processing liquid comprising:
 - i. at least one inorganic salt, and
 - ii. at least one lubricant, wherein the solid matter weight ratio of said lubricant to said inorganic salt is within the range of 0.1 to 4.0,
 - c. forming a lubricant film on the metal wire rod by drying the metal wire rod immediately after step (b);wherein all steps are in a continuous inline system and said metal wire rod is not subjected to chemical conversion treatment or coating.
2. (Original) The method of manufacturing metal wire rod for use in plastic working of claim 1 further comprising the step of pre-heating the metal wire rod prior to contacting with the aqueous, lubricating-coating formation processing liquid in step (b).
3. (Original) The method of manufacturing metal wire rod for use in plastic working of claim 1 wherein the inorganic salt is selected from the group consisting of phosphates, sulfates, borates, silicates, molybdates, and

Serial No. 10/827,174
Art Unit: 1762

tungstates.

4. (Original) The method of manufacturing metal wire rod for use in plastic working of claim 3 wherein the lubricant is selected from the group consisting of metal soaps, waxes, poly-tetrafluoroethylene, molybdenum disulfide, and graphite.
5. (Cancelled)
6. (Original) The method of manufacturing metal wire rod for use in plastic working according to Claim 5, wherein the metal wire rod has a diameter of 0.3–50 mm.
7. (Original) The method of manufacturing metal wire rod for use in plastic working according to Claim 1, wherein the line speed for continuous processing of the metal wire rod is in the range of 10- 150 m/minute.
8. (Original) The method of manufacturing metal wire rod for use in plastic working according to Claim 4, wherein the aqueous, lubricating-coating formation processing liquid further comprises one or more surfactants selected from the group consisting of nonionic surfactants, anionic surfactants, amphoteric surfactants, and cationic surfactants.
9. (Original) The method of manufacturing metal wire rod for use in plastic

Serial No. 10/827,174**Art Unit: 1762**

working according to Claim 5, wherein the solid matter weight ratio of said lubricant to said inorganic salt is within the range of 0.2 to 1.5.

10. (Currently Amended) The method of manufacturing metal wire rod for use in plastic working of claim 21 4, wherein the at least one cleaning process is selected from the group consisting of shot blasting, sand blasting, bending, anodic pickling, and cathodic pickling.
11. (Original) The method of manufacturing metal wire rod for use in plastic working of claim 1, wherein said metal wire rod is metal selected from the group consisting of iron, steel, stainless steel, aluminum, aluminum alloy, magnesium, magnesium alloy, titanium, titanium alloy, copper, and copper alloy.
12. (Original) The method of manufacturing metal wire rod for use in plastic working according to Claim 11, wherein the line speed for continuous processing of the metal wire rod is in the range of 10- 150 m/minute.
13. (Currently Amended) A method of manufacturing metal wire rod for use in plastic working comprising:

cleaning, coating and drying said metal wire rod in a continuous inline system, without chemical conversion treatment or coating, said system comprising the steps of:

Serial No. 10/827,174**Art Unit: 1762**

- a. cleaning metal wire rod by at least one cleaning process for 20 seconds or less;
 - b. preheating the metal wire rod and immediately thereafter contacting said metal wire rod for 5 seconds or less with an aqueous, lubricating-coating formation processing liquid comprising:
 - i. at least one inorganic salt selected from the group consisting of phosphates, sulfates, borates, silicates, molybdates, and tungstates, and
 - ii. at least one lubricant selected from the group consisting of metal soaps, waxes, poly-tetrafluoroethylene, molybdenum disulfide, and graphite, in the absence of polymer different from (ii.);
 - c. forming a lubricant film with a coating weight of 0.5-20 g/m² on the metal wire rod by drying the metal wire rod immediately after step (b).
14. (Original) The method of manufacturing metal wire rod for use in plastic working according to Claim 13, wherein the metal wire rod has a diameter of 0.3-50 mm.
15. (Original) The method of manufacturing metal wire rod for use in plastic working according to Claim 13, wherein the line speed for continuous processing of the metal wire rod is in the range of 10- 150 m/minute.
16. (Original) The method of manufacturing metal wire rod for use in plastic working according to Claim 13, wherein the aqueous, lubricating-coating

Serial No. 10/827,174**Art Unit: 1762**

formation processing liquid further comprises one or more surfactants selected from the group consisting of nonionic surfactants, anionic surfactants, amphoteric surfactants, and cationic surfactants.

17. (Original) The method of manufacturing metal wire rod for use in plastic working according to Claim 13, wherein the solid matter weight ratio of said lubricant to said inorganic salt is within the range of 0.1 to 4.0.
18. (Original) The method of manufacturing metal wire rod for use in plastic working according to Claim 17, wherein the solid matter weight ratio of said lubricant to said inorganic salt is within the range of 0.2 to 1.5.
19. (Original) The method of manufacturing metal wire rod for use in plastic working of claim 13, wherein the at least one cleaning process is selected from the group consisting of shot blasting, sand blasting, bending, anodic pickling, and cathodic pickling.
20. (Original) The method of manufacturing metal wire rod for use in plastic working of claim 13, wherein said metal wire rod is metal selected from the group consisting of iron, steel, stainless steel, aluminum, aluminum alloy, magnesium, magnesium alloy, titanium, titanium alloy, copper, and copper alloy.
21. (Currently Amended) A method of manufacturing metal wire rod for use in

Serial No. 10/827,174

Art Unit: 1762

plastic working comprising:

- a. cleaning metal wire rod by at least one cleaning process for 20 seconds or less;
- b. contacting the metal wire rod for 5 seconds or less with an aqueous, lubricating-coating formation processing liquid consisting essentially of:
 - i. at least one inorganic salt selected from the group consisting of phosphates, sulfates, borates, silicates, molybdates, and tungstates.
 - ii. at least one lubricant selected from the group consisting of metal soaps, waxes, polytetrafluorethylene, molybdenum disulfide, and graphite, wherein the solid matter weight ratio of said lubricant to said inorganic salt is within the range of 0.1 to 4.0, and
 - iii. optionally, a surfactant and/or a thickening agent, said thickening agent selected from inorganic and polysaccharide thickening agents,
- c. forming a lubricant film on the metal wire rod by drying the metal wire rod immediately after step (b);

wherein all steps are in a continuous inline system.

22. (Previously Presented) The method of manufacturing metal wire rod for use in plastic working of claim 21, wherein solid matter concentration of the aqueous, lubricating-coating formation processing liquid ranges from 5 to 15 weight percent.